



Natural Kraft Board

Containerboard											
Cedar Springs Linerboard Specifications(Metric Units)											
Natural Kraft Linerboard											
Test Performed	Units										
Basis weight	g/m²	127 121-133	161 153-169	200 190-214.3	225 218-245.6	250 238.8-267	270 255-287.5	300 285-321.2	337 320-360.3	400 380.3-428	440 417-470.1
Moisture	%	5.0-9.0	5.0-9.0	5.0-9.0	5.0-9.0	5.0-9.0	5.0-9.0	5.0-9.0	5.0-9.0	5.0-9.0	5.0-9.0
Mullen(min)	kPa	512	552	689	799.2	813	840.6	895.7	964.6	1068	1136.9
Porosity(min)	sec/ 100ml	8	8	8	8	8	8	8	8	8	8
Slide Angle	degrees	20-40	20-40	20-40	20-40	20-40	20-40	20-40	20-40	20-40	20-40

All Tests are Based TAPPI Test Methods Performed Under TAPPI Standard Conditions

Hercules Size Test is Performed using 20% formic acid